

CRYOTECH CMA40®

Solid Commercial Deicer

Why CMA40?

Cryotech CMA40 is a blend of calcium magnesium acetate (Cryotech CMA) and sodium chloride (salt). The product contains not less than 40% Cryotech CMA. Independent studies have shown that when Cryotech CMA is mixed with salt, Cryotech CMA is an effective corrosion inhibitor. Ideal for situations where protection from concrete spalling is needed, but limited quantities of salt can be tolerated, CMA40 lasts longer than straight chlorides.

BENEFITS

- Significantly less corrosive than salt to exposed steel or steel reinforcement
- Minimizes spalling, less concrete damage
- Retains many CMA benefits, safe for high quality concrete
- Requires fewer applications than other common deicers
- Complimentary customer training upon request

PERFORMANCE

- Like sodium chloride, works best above 20°F (-7°C)
- Long lasting effect, better than chloride salts
- Effectively breaks and inhibits the bond between snow/ice and pavement

ENVIRONMENT

- CMA components are readily biodegradable
- Increases soil permeability, calcium and magnesium are soil amendments

APPLICATION


- Apply early in the storm to prevent snow/ice bonding
- First application: ~10 lbs/1000ft² (50 g/m²)
- Wait at least 20 minutes to remove snow/ice
- Re-apply when new snow/ice accumulation shows first tendency to bond
- Plow regularly



CRYOTECH CMA40® PRODUCT SPECIFICATIONS

COMPOSITION	APPEARANCE	BULK DENSITY
40% Calcium Magnesium Acetate (CMA) minimum 60% sodium chloride (NaCl)	CMA, white to off-white spherical pellet NaCl, white crystalline solids	57 lbs/ft ³ to 61 lbs/ft ³ (0.9 g/cm ³ to 1.0 g/cm ³)
TYPICAL pH	PACKAGING	HANDLING
8 to 10 in a 10% solution	<ul style="list-style-type: none"> • 55 lbs (25 kg) poly bags - 40 bag minimum • 2205 lbs (1000 kg) Super Sacks - 1 super sack minimum • Bulk - 20 metric ton minimum 	<ul style="list-style-type: none"> • Store in original container • Avoid excess moisture which may cause caking • Preserve pellet integrity by not overhandling • Apply with the same equipment as salt

Effect of CMA Blended Deicers on Concrete



TO ORDER OR FOR PRODUCT INFORMATION CONTACT:

Ph: +1 319.372.6012 or +1 800.346.7237 Fax: +1 319.372.2662 E-mail: deicers@cryotech.com

Cryotech Deicing Technology . 6103 Orthoway . Fort Madison, IA 52627 . www.cryotech.com

Form #MKT500 Rev. 8/1/2019